

Technical Datasheet

Precision Lift™ 4.75#



Two-component structural polyurethane foam

Description

Precision Lift 4.75# is a two-component, polyurethane foam used for concrete slab lifting and stabilizing, undersealing concrete slabs, compaction grouting of soil, and filling voids behind pipes, walls, manholes and other structures. This closed-cell, high density structural foam is hydro insensitive and can be used in wet or dry environments.

Primary Applications

- Concrete highways
- Airport runways and taxiways
- Bridge approach slabs
- Concrete slabs
- Concrete pipes
- Utility vaults

Packaging

- 100 gallon units (drums)
- 550 gallon units (totes)
- 660 gallon units

Advantages

- Quick set time
- Low viscosity
- Hydro insensitive
- Bonds with soil and concrete
- Designed to efficiently develop hydraulic lift to level and stabilize concrete slabs and foundations
- Lower cost alternative vs replacement
- Lighter weight than mudjacking
- Lift can be executed to precise measures

Weight

- A side: 10.258 lb/gallon
- B side: 8.697 lb/gallon

Technical information: Physical properties at 73°F (23°C) - Liquid

Properties will vary depending upon site conditions, application method, mixing method and equipment, material temperature, and curing conditions.

Solids content: 100%

Viscosity: 270-280 centipoise

Note: Viscosity scale for Prime Resins products: 50 and under= super low, 51-100= very low, 101-400= low, and 401-1000=

Physical Properties - Cured	Results	Test Method
Compressive strength	100 psi or 14,00 psf	ASTM D-1621
Tensile strength	100 psi	ASTM D-638
Expansion	15x (unconfined)	
Density	4.5 - 5.0 lbs/cubic ft	ASTM D-1622
Shrinkage	None	ASTM D-1042 / D-756

Reaction times	
Cream time	20 seconds
Tack free time	45 seconds
85% full strength	15 minutes

Head Office: 2291 Plunkett Road, Conyers, GA 30012

T: 770-388-0626 F: 770-388-0936 W: www.primeresins.com

E: info@primeresins.com

A Company

Technical Datasheet



Accessory Products

- Eco Flush
- Pumps
- Equalizer gun
- Soil probes
- Pipe jack
- Turnkey trailer rig

Directions For Use

Mixing Ratio: A:B 1:1 by volume

Material Preparation: Store material overnight to precondition to 70-80°F (21-27°C) prior to use. Pre-mix the “B” component prior to combining. “B” component contains chemicals that settle over time. Failure to properly pre-mix will result in uncured or improperly cured material.

Limitations: Cold temperatures will slow down reaction time and increase viscosity. pH below 3 or above 10 may adversely affect foam properties.

Storage & Clean Up

Storage: Store in dry environment between 40° and 80°F (4-27°C). Shelf Life: 1 year from date of manufacture in unopened containers properly stored. Protect from moisture.

Clean Up: Clean off of skin with soap and water. To clean uncured resin from the gun, flush with acetone. Remove cured material by soaking in Prime Flex CGC (not appropriate for contact with plastic).

Environmental Protection

Cured material is environmentally safe. Dispose of in according to appropriate regulations. Clean up any spilled catalyzed liquid material and add a small amount of water to cure unreacted material.

Shipping

Shipping Class: Motor Freight Class 60

Hazard Classification: Not Hazardous

Health & Safety

Safety: Use OSHA-approved personal protective equipment (PPE), including safety glasses, gloves and confined space equipment/procedures if applicable. Avoid skin contact; do not ingest. See SDS for complete safety precautions. For professional use only .

First Aid

Eye Contact: Immediately flush with large amounts of water.

Seek medical attention. **Inhalation:** Move to fresh air if symptoms occur. If breathing is difficult, seek medical attention. **Ingestion:** Seek medical attention immediately.

Skin Contact: Wipe off contaminated area and wash with soap and water immediately.

Manufacturing

Products are manufactured by Prime Resins, Inc. in the U.S.A. under strict quality assurance practices at our Conyers, GA plant.

Warranty & Disclaimer

Prime Resins, Inc. warrants its products to be free from manufacturing defects and that products meet the published characteristics when tested in accordance with ASTM and Prime Resins standards. No other warranties by Prime Resins, Inc. are expressed or implied, including no warranty of merchantability or fitness for a particular purpose. Prime Resins, Inc. will not be liable for damages of any sort resulting from any claimed breach of warranty. Prime Resins' liability under this warranty is limited to replacement of material or refund of sales price of the material. There are no warranties on any product that has exceeded the “shelf life” or “expiration date” printed on the package label.