

# Technical Datasheet

## Prime Rez 1200 Low Mod LV



Extremely low viscosity epoxy injection resin

### Description

Prime Rez 1200 is a two-component, very low viscosity epoxy resin for structural repair, designed to be injected or gravity fed into cracks in concrete, masonry or stone that are subject to shock or vibration. Conforms to ASTM C-881 type II and III, grade 1, class B and C.

### Primary Applications

- Concrete walls and floors
- Concrete tanks
- Dams
- Parking decks
- Bridges
- Retaining walls
- Foundation walls, etc.

### Advantages

- High compressive, bond, tensile and flexural strengths
- Very low viscosity
- Good chemical resistance

### Packaging

- 1-1/2 gallon
- 3 gallon units
- 15 gallon units
- 2:1 Quick Mix cartridges—case of 10

### Technical information: Physical properties at 73°F (23°C) - Liquid

Properties will vary depending upon site conditions, application method, mixing method and equipment, material temperature, and curing conditions.

**Solids content:** 100% solids, no VOCs

**Viscosity:** 70 - 90 centipoise

**Color:** Amber (clear)

*Note: Viscosity scale for Prime Resins products: 50 and under= super low, 51-100= very low, 101-400= low, and 401-1000= moderate viscosity.*

Pot Life	100 Grams	1 Gallon	20 Mils
90°F (32°C)	15 min	11 min	2 hr 10 min
73°F (23°C)	30 min	23 min	8 - 12 hours
50°F (10°C)	1 hr 15 min	1 hour	12 - 15 hours
Test results			
Compressive strength	6,120		ASTM D-695
Compressive modulus of elasticity	139,000		ASTM D-695
Tensile strength	4,230		ASTM D-638
Tensile modulus of elasticity	147,000		ASTM D-638
Tensile elongation	35%		ASTM D-638
Bond strength (dry cure) - 2 day	1,940		ASTM C-882
Bond strength (dry cure) - 14 day	2,900		ASTM C-882

Test results (cont.)		
Flexural strength	2,760	ASTM D-790
Shore hardness	70 D	D scale
Water absorption	1.5%	ASTM D-570

## Accessory Products

- Prime Gel 2000
- Prime Gel 2100
- Prime Gel 2500 (for surface seal)
- Injection ports

## Directions For Use

*Mixing Ratio:* A:B 2:1 by volume

*Manual Mixing:* Pre-mix each component prior to combining. Only mix the amount of material that can be used within the pot life. Thoroughly mix materials using a low speed drill with a mixing paddle. Scrape the sides and bottom of the pail while mixing. Note: Larger batches exotherm and set up faster than small batches.

*Pump Application:* This product is ideally suited for use with a two-component injection pump or Quick Mix cartridge system.

*Material Preparation:* Store material overnight to precondition to 70-80°F (21-27°C) prior to use.

*Limitations:* Cold temperatures will slow down reaction time and increase viscosity. Do not use below 32°F (0°C) as ice crystals in the concrete will inhibit bond. Material that is off ratio or not mixed thoroughly will not cure to full strength and may remain tacky indefinitely.

## Storage & Clean Up

*Storage:* Store in dry environment between 40 and 80°F (4 and 27°C). Do not allow to freeze. Shelf Life: 1 year from date of manufacture in unopened containers properly stored. Protect from moisture.

*Clean Up:* Clean off of skin with soap and water immediately.

## Environmental Protection

Cured material is environmentally safe. Dispose of in according to appropriate regulations. Clean up any spilled catalyzed liquid material and dispose of according to local, state and federal regulations.

## Shipping

Shipping Class: Motor Freight Class 60  
Hazard Classification: DOT 8

## Health & Safety

*Safety:* "B" component contains amines and may cause severe burns upon skin contact for any length of time. Use OSHA-approved personal protective equipment (PPE), including safety glasses, gloves and confined space equipment/procedures if applicable. Avoid skin contact; do not ingest. See SDS for complete safety precautions. For professional use only.

### First Aid

**Eye Contact:** Immediately flush with large amounts of water.

Seek medical attention. **Inhalation:** Move to fresh air if symptoms occur. If breathing is difficult, seek medical attention. **Ingestion:** Seek medical attention immediately.

**Skin Contact:** Wipe off contaminated area and wash with soap and water immediately.

## Manufacturing

Products are manufactured by Prime Resins, Inc. in the U.S.A. under strict quality assurance practices at our Conyers, GA plant.

## Warranty & Disclaimer

Prime Resins, Inc. warrants its products to be free from manufacturing defects and that products meet the published characteristics when tested in accordance with ASTM and Prime Resins standards. No other warranties by Prime Resins, Inc. are expressed or implied, including no warranty of merchantability or fitness for a particular purpose. Prime Resins, Inc. will not be liable for damages of any sort resulting from any claimed breach of warranty. Prime Resins' liability under this warranty is limited to replacement of material or refund of sales price of the material. There are no warranties on any product that has exceeded the "shelf life" or "expiration date" printed on the package label.